



PC 11-010

is a solvent free, single-component polyurethane primer. It is designed for the adhesion between asphalt, concrete and elastic layers and between elastic layers (retopping).

Density	@ 23 °C	1.00 ± 0.02 g/cm ³
Viscosity	@ 23 °C	300 ± 70 mPas
Colour		transparent
Curing Time	@ 20 °C; 50 % relative humidity	4 to 6 hours
Flash point		62 °C
NCO-content		8 ± 0,5 %
Processing temperature		min. 10 °C

Installation guidelines

Open time of the applied primer is about 4-6 hours. If this period is exceeded, apply a new primer coat to achieve an optimum adhesion.

PC 11-010 is moisture-sensitive. To obtain a uniform coverage, apply PC 11-010 at a rate of 100-150 g/m².

If less primer is applied, adhesion decreases; exceeding the recommended amount may damage the asphalt.

Safety guidelines

Never use PC 11-010 near flames or open light. Smoking is also strictly prohibited during the application process. Wear approved eye protection and gloves during application. Adequate ventilation or use of a respirator is required in enclosed spaces.

We recommend Polycomp cleaner (PC 11-040 – Butyl acetate) for the cleaning of the equipment.

Packaging

200 kg drum, 25 kg pail

Storage

Store PC 11-010 in a dry and cool place but not below 10 °C. Shelf life of product stored in original unopened containers is 6 months. Close partial containers carefully, protected against moisture and use as soon as possible.